

Techmer ES HiFill[®] PA6 L N YL038MB

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Nucleated

Material Notes:

Availability: North America Forms: Pellets Additive: Lubricant, UV Stabilizer and Nucleating Agent Features: Lubricated, Fast Molding Cycle, Good Processability, Good UV Resistance and Nucleated Appearance: Yellow Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA6-L-N-YL038MB.php

Physical Properties	Metric	English	Comments
Density	1.13 g/cc	0.0408 lb/in ³	ASTM D792
Water Absorption	2.8 % @Time 86400 sec	2.8 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.013 cm/cm @Thickness 3.17 mm	0.013 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	119	119	ASTM D785
Tensile Strength, Yield	90.3 MPa	13100 psi	ASTM D638
Elongation at Break	70 %	70 %	ASTM D638
Flexural Strength	115 MPa	16700 psi	ASTM D790
Flexural Modulus	2.83 GPa	410 ksi	ASTM D790
Izod Impact, Notched	0.454 J/cm @Thickness 3.17 mm	0.850 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	82.8 Åµm/m-Å°C	46.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	178 Å°C	352 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	76.7 Å°C	170 Å°F	Unannealed; ASTM D648
Flammability, UL94	V-2	V-2	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+13 ohm-cm	1.00e+13 ohm-cm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China