

Techmer ES HiFill® PA6/6 GF13 TL10 13% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 10% Glass Fiber Filled , Nylon 66, PTFE Filled

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 13% Filler by Weight Additive: PTFE Lubricant (10%) Features: Lubricated Appearance: Natural Color Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA66-GF13-TL10-13-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.30 g/cc	0.0470 lb/in ³	ASTM D792
Water Absorption	0.95 %	0.95 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0060 cm/cm	0.0060 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	103 MPa	15000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	152 MPa	22000 psi	ASTM D790
Flexural Modulus	4.83 GPa	700 ksi	ASTM D790
Izod Impact, Notched	0.587 J/cm	1.10 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	32.4 Åµm/m-Å°C	18.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	255 Å°C	491 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	221 Å°C	430 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	19.3 kV/mm	490 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China