

## Techmer ES HiFill® PA6/6 GF33 HS L BK001 33% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Heat Stabilized

### Material Notes:

Availability: North America  
Forms: Pellets  
Filler/Reinforcement: Glass Fiber Reinforcement, 33% Filler by Weight  
Additive: Lubricant and Heat Stabilizer  
Features: Lubricated and Heat Stabilized  
Appearance: Black  
Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-HiFill-PA66-GF33-HS-L-BK001-33-Glass-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA66-GF33-HS-L-BK001-33-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in <sup>3</sup>	ASTM D792
Water Absorption	1.8 % @Time 86400 sec	1.8 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 cm/cm @Thickness 3.17 mm	0.0050 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	159 MPa	23000 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	241 MPa	35000 psi	ASTM D790
Flexural Modulus	9.65 GPa	1400 ksi	ASTM D790
Izod Impact, Notched	0.854 J/cm @Thickness 3.17 mm	1.60 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	19.8 Åµm/m-Å°C	11.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	254 Å°C	490 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	249 Å°C	480 Å°F	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	19.3 kV/mm	490 kV/in	Method A (Short-Time); ASTM D149

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**