

Techmer ES HiFill® PA6/6 GF33 NAT001 Y 33% Glass Filled (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Heat Stabilized

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber Reinforcement, 33% Filler by Weight
Additive: Lubricant and Heat Stabilizer
Features: Lubricated and Heat Stabilized
UL File Number: E157318
Appearance: Natural Color
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PA66-GF33-NAT001-Y-33-Glass-Filled-Conditioned.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	ASTM D792
Water Absorption	1.8 % @Time 86400 sec	1.8 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0050 cm/cm @Thickness 3.17 mm	0.0050 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	172 MPa	25000 psi	ASTM D638
Elongation at Break	6.0 %	6.0 %	ASTM D638
Flexural Strength	207 MPa	30000 psi	ASTM D790
Flexural Modulus	7.58 GPa	1100 ksi	ASTM D790
Izod Impact, Notched	1.28 J/cm @Thickness 3.17 mm	2.40 ft-lb/in @Thickness 0.125 in	ASTM D256

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China