

## Techmer ES HiFill® PC GF10 10% Glass Filled

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate, 10% Glass Filled

### Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 10% Filler by Weight Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-HiFill-PC-GF10-10-Glass-Filled.php](http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PC-GF10-10-Glass-Filled.php)

Physical Properties	Metric	English	Comments
Density	1.25 g/cc	0.0452 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.12 % @Time 86400 sec	0.12 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0035 cm/cm @Thickness 3.17 mm	0.0035 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	124	124	ASTM D785
Tensile Strength, Yield	66.9 MPa	9700 psi	ASTM D638
Elongation at Break	8.0 %	8.0 %	ASTM D638
Flexural Strength	110 MPa	16000 psi	ASTM D790
Flexural Modulus	3.45 GPa	500 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 3.17 mm	2.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	32.4 Åµm/m-Å°C	18.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	146 Å°C	295 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	143 Å°C	290 Å°F	Unannealed; ASTM D648
Flammability, UL94	V-2	V-2	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+17 ohm-cm	1.00e+17 ohm-cm	ASTM D257

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China