

Techmer ES HiFill[®] PP 0112 B AM2 Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Unspecified Filler/Reinfor
Additive: Antimicrobial (Fungicide)
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PP-0112-B-AM2-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ASTM D792
Water Absorption	0.050 % @Time 86400 sec	0.050 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.015 cm/cm @Thickness 3.17 mm	0.015 in/in @Thickness 0.125 in	ASTM D955
Melt Flow	4.0 g/10 min @Load 2.16 kg, Temperature 230 °C	4.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	95	95	ASTM D785
Tensile Strength, Yield	20.7 MPa	3000 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Flexural Strength	35.9 MPa	5200 psi	ASTM D790
Flexural Modulus	2.41 GPa	350 ksi	ASTM D790
Izod Impact, Notched	0.267 J/cm @Thickness 3.17 mm	0.500 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	34.2 µm/m-°C	19.0 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	107 °C	225 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	62.8 °C	145 °F	Unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China