

Techmer ES HiFill® PP CO GF30 CC 30% Glass Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer , Polypropylene with 30% Glass Fiber Filler

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber Reinforcement, 30% Filler by Weight
Features: Copolymer and Chemically Coupled
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PP-CO-GF30-CC-30-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ASTM D792
Water Absorption	0.050 %	0.050 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0040 cm/cm	0.0040 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	100	100	ASTM D785
Tensile Strength, Yield	71.7 MPa	10400 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	107 MPa	15500 psi	ASTM D790
Flexural Modulus	5.86 GPa	850 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm	1.00 ft-lb/in	ASTM D256
	@Thickness 3.17 mm, Temperature -28.9 °C	@Thickness 0.125 in, Temperature -20.0 °F	
	2.46 J/cm	4.60 ft-lb/in	ASTM D256
	@Thickness 3.17 mm, Temperature 22.8 °C	@Thickness 0.125 in, Temperature 73.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	37.8 µm/m-°C	21.0 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	157 °C	315 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	132 °C	270 °F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Thermal Properties

Metric

English

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China