

Techmer ES HiFill[®] PP GB50 50% Glass Beads Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Glass Bead Filled

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Bead, 50% Filler by Weight
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PP-GB50-50-Glass-Beads-Filled.php

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in ³	ASTM D792
Water Absorption	0.030 % @Time 86400 sec	0.030 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0090 cm/cm @Thickness 3.17 mm	0.0090 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	99	99	ASTM D785
Tensile Strength, Yield	18.6 MPa	2700 psi	ASTM D638
Elongation at Yield	8.0 %	8.0 %	ASTM D638
Flexural Yield Strength	29.6 MPa	4300 psi	ASTM D790
Flexural Modulus	2.28 GPa	330 ksi	ASTM D790
Izod Impact, Notched	0.320 J/cm @Thickness 3.17 mm	0.600 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	61.2 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	34.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Melting Point	170 $\text{Å}^\circ\text{C}$	338 $\text{Å}^\circ\text{F}$	
Deflection Temperature at 0.46 MPa (66 psi)	121 $\text{Å}^\circ\text{C}$	250 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	79.4 $\text{Å}^\circ\text{C}$	175 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China