

Techmer ES HiFill® PP LGF50 CC NAT 12mm 50% Glass Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 50% Glass Fiber Filler

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Long Glass Fiber, 50% Filler by Weight
Features: Chemically Coupled
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PP-LGF50-CC-NAT-12mm-50-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.32 g/cc	0.0477 lb/in ³	ASTM D792
Water Absorption	0.060 % @Time 86400 sec	0.060 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	112	112	ASTM D785
Tensile Strength, Yield	128 MPa	18500 psi	ASTM D638
Elongation at Yield	4.0 %	4.0 %	ASTM D638
Flexural Yield Strength	179 MPa	26000 psi	ASTM D790
Flexural Modulus	8.96 GPa	1300 ksi	ASTM D790
Izod Impact, Notched	2.03 J/cm @Thickness 3.17 mm	3.80 ft-lb/in @Thickness 0.125 in	ASTM D256
Izod Impact, Unnotched	7.47 J/cm @Thickness 3.17 mm	14.0 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	21.6 Åµm/m-Å°C	12.0 Åµin/in-Å°F	ASTM D696
Melting Point	163 Å°C	325 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	163 Å°C	325 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	154 Å°C	310 Å°F	Unannealed; ASTM D648

Flammability UL 94 Thermal Properties	HB Metric	HB English	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	2.00e+16 ohm-cm	2.00e+16 ohm-cm	ASTM D257
Dielectric Strength	20.1 kV/mm	510 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China