

Techmer ES HiFill[®] PSU GF20 BK 20% Glass Filled

Category : Polymer , Thermoplastic , Polysulfone (PSU) , Polysulfone, 20% Glass Fiber Reinforced

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber Reinforcement, 20% Filler by Weight Appearance:

Black Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-HiFill-PSU-GF20-BK-20-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.38 g/cc	0.0499 lb/in ³	ASTM D792
Water Absorption	0.24 % @Time 86400 sec	0.24 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0020 cm/cm @Thickness 3.17 mm	0.0020 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	123	123	ASTM D785
Tensile Strength, Yield	112 MPa	16200 psi	ASTM D638
Elongation at Break	7.0 %	7.0 %	ASTM D638
Flexural Yield Strength	153 MPa	22200 psi	ASTM D790
Flexural Modulus	5.86 GPa	850 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm @Thickness 3.17 mm	1.50 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	30.6 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	17.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	182 $\text{Å}^\circ\text{C}$	360 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Strength	16.9 kV/mm	430 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China