

Techmer ES Luriblend® HIPS E SL5

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Availability: North America Forms: Pellets Additive: Silicone Lubricant (5%) Appearance: Natural Color Processing Method:

Extrusion Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-HIPS-E-SL5.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	ASTM D792
Water Absorption	0.60 % @Time 86400 sec	0.60 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0040 cm/cm @Thickness 3.17 mm	0.0040 in/in @Thickness 0.125 in	ASTM D955
Melt Flow	2.0 g/10 min @Load 1.20 kg, Temperature 230 °C	2.0 g/10 min @Load 2.65 lb, Temperature 446 °F	ASTM D1238
	33 g/10 min @Load 3.80 kg, Temperature 230 °C	33 g/10 min @Load 8.38 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	60	60	ASTM D785
Tensile Strength, Yield	26.2 MPa	3800 psi	ASTM D638
Elongation at Break	44 %	44 %	ASTM D638
Flexural Strength	34.5 MPa	5000 psi	ASTM D790
Flexural Modulus	1.45 GPa	210 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 3.17 mm	2.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	63.0 µm/m-°C	35.0 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	96.1 °C	205 °F	Unannealed; ASTM D648

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (100 psi)	85.0 °C	185 °F	1; ASTM D648
Flammability, UL94	HB	HB	
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China