

## Techmer ES Luriblend<sup>®</sup> HTN 05007

Category : Polymer , Thermoplastic , Nylon , High Temperature Nylon

### Material Notes:

Availability: North America Forms: Pellets Additive: Heat Stabilizer and Lubricant Features: Heat Stabilized, High Heat Resistance and Lubricated Appearance: Black Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Luriblend-HTN-05007.php](http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-HTN-05007.php)

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.25 % @Time 86400 sec	0.25 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.016 cm/cm @Thickness 3.17 mm	0.016 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	114	114	ASTM D785
Tensile Strength, Yield	67.6 MPa	9800 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Flexural Strength	96.5 MPa	14000 psi	ASTM D790
Flexural Modulus	2.28 GPa	330 ksi	ASTM D790
Izod Impact, Notched	0.427 J/cm @Thickness 3.17 mm	0.800 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	84.6 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	47.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	224 $\text{Å}^\circ\text{C}$	435 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	121 $\text{Å}^\circ\text{C}$	250 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Flammability, UL94	V-2	V-2	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257

Electrical Properties

Metric 14 ohm

English 4 ohm

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China