

Techmer ES Luriblend[®] PA6 GL15 Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

Availability: North America Forms: Pellets Additive: Graphite Powder Lubricant(15%) Features: Lubricated Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-PA6-GL15-Nylon-6.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ASTM D792
Water Absorption	1.0 % @Time 86400 sec	1.0 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.0090 cm/cm @Thickness 3.17 mm	0.0090 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	118	118	ASTM D785
Tensile Strength, Yield	65.5 MPa	9500 psi	ASTM D638
Elongation at Break	8.0 %	8.0 %	ASTM D638
Flexural Strength	93.1 MPa	13500 psi	ASTM D790
Flexural Modulus	3.65 GPa	530 ksi	ASTM D790
Izod Impact, Notched	0.374 J/cm @Thickness 3.17 mm	0.700 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	59.4 Åµm/m-Å°C	33.0 Åµin/in-Å°F	ASTM D696
Melting Point	220 Å°C	428 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	188 Å°C	370 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	82.2 Å°C	180 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China