

Techmer ES Luriblend[®] PA6/6 GF33 TL15 33% Glass Filled

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled , Nylon 66, Heat Stabilized , Nylon 66, PTFE Filled

Material Notes:

Availability: North America Forms: Pellets Filler/Reinforcement: Glass Fiber, 33% Filler by Weight Additive: Heat Stabilizer and PTFE

Lubricant(15%) Features: Lubricated, Good Wear Resistance, Heat Stabilized and Low Friction Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-PA66-GF33-TL15-33-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.50 g/cc	0.0542 lb/in ³	ASTM D792
Water Absorption	0.50 %	0.50 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Flow	0.0050 cm/cm	0.0050 in/in	ASTM D955
	@Thickness 3.17 mm	@Thickness 0.125 in	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	90	90	ASTM D785
Tensile Strength, Yield	149 MPa	21600 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Flexural Strength	224 MPa	32500 psi	ASTM D790
Flexural Modulus	8.96 GPa	1300 ksi	ASTM D790
Izod Impact, Notched	0.801 J/cm	1.50 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	
Coefficient of Friction, Dynamic	0.28	0.28	0.22
Coefficient of Friction, Static	0.20	0.20	ASTM D1894
K (wear) Factor	36.3 x 10 ⁻⁸ mm ³ /N-M	18.0 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	
Limiting Pressure Velocity	0.613 MPa-m/sec	17500 psi-ft/min	10 fpm
	0.613 MPa-m/sec	17500 psi-ft/min	1000 fpm
	0.701 MPa-m/sec	20000 psi-ft/min	100 fpm

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

CTE, linear, Parallel to Flow Thermal Properties	18.0 Åum/m-Å°C Metric	10.0 Åuin/in-Å°F English	ASTM D696 Comments
Deflection Temperature at 0.46 MPa (66 psi)	259 Å°C	498 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	254 Å°C	490 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	21.7 kV/mm	550 kV/in	Method A (Short-Time); ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China