

Techmer ES Luriblend® POM CO GF10 TL10 BK 10% Glass Filled

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, 10% Glass Fiber Reinforced , Acetal Copolymer, PTFE Filled

Material Notes:

Availability: North America
Forms: Pellets
Filler/Reinforcement: Glass Fiber, 10% Filler by Weight
Additive: PTFE Lubricant(10%)
Features: Lubricated, Copolymer, Good Wear Resistance and Low Friction
Appearance: Black
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-POM-CO-GF10-TL10-BK-10-Glass-Filled.php

Physical Properties	Metric	English	Comments
Density	1.53 g/cc	0.0553 lb/in ³	ASTM D792
Water Absorption	0.10 % @Time 86400 sec	0.10 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.012 cm/cm @Thickness 3.17 mm	0.012 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D785
Tensile Strength, Yield	72.4 MPa	10500 psi	ASTM D638
Elongation at Break	2.5 %	2.5 %	ASTM D638
Flexural Strength	117 MPa	17000 psi	ASTM D790
Flexural Modulus	4.27 GPa	620 ksi	ASTM D790
Izod Impact, Notched	0.534 J/cm @Thickness 3.17 mm	1.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	66.6 Åm/m-Å°C	37.0 Åin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	168 Å°C	335 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	163 Å°C	325 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China