

## Techmer ES Luriblend<sup>®</sup> POM CO TL10 Acetal

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, PTFE Filled

### Material Notes:

Availability: North America Forms: Pellets Additive: PTFE Lubricant(10%) Features: Lubricated, Good Wear Resistance, Low Friction and Copolymer Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Luriblend-POM-CO-TL10-Acetal.php](http://www.lookpolymers.com/polymer_Techmer-ES-Luriblend-POM-CO-TL10-Acetal.php)

Physical Properties	Metric	English	Comments
Density	1.45 g/cc	0.0524 lb/in <sup>3</sup>	ASTM D792
Water Absorption	0.17 % @Time 86400 sec	0.17 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage, Flow	0.018 cm/cm @Thickness 3.17 mm	0.018 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	92	92	ASTM D785
Tensile Strength, Yield	60.7 MPa	8800 psi	ASTM D638
Elongation at Break	9.0 %	9.0 %	ASTM D638
Flexural Strength	75.8 MPa	11000 psi	ASTM D790
Flexural Modulus	2.69 GPa	390 ksi	ASTM D790
Izod Impact, Notched	0.481 J/cm @Thickness 3.17 mm	0.900 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	50.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	100 $\text{Å}^\circ\text{C}$	212 $\text{Å}^\circ\text{F}$	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Dielectric Strength	17.7 kV/mm	450 kV/in	Method A (Short-Time); ASTM D149

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**