

Techmer ES Plaslube® J-4/30/TF/13/SI/2 NAT PA6/12

Category : Polymer , Thermoplastic , Nylon , Nylon 612 , Nylon 612, Glass Fiber Filler

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Plaslube-J-430TF13SI2-NAT-PA612.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.42 g/cc	1.42 g/cc	ASTM D792
Water Absorption	0.13 %	0.13 %	24 Hrs; ASTM D570
Linear Mold Shrinkage	0.0020 cm/cm	0.0020 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	138 MPa	20000 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	197 MPa	28500 psi	ASTM D790
Flexural Modulus	8.34 GPa	1210 ksi	ASTM D790
Compressive Strength	124 MPa	18000 psi	ASTM D695
Izod Impact, Notched	1.23 J/cm	2.30 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	48.6 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 20.0 $\text{Å}^\circ\text{C}$	27.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 68.0 $\text{Å}^\circ\text{F}$	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	199 $\text{Å}^\circ\text{C}$	390 $\text{Å}^\circ\text{F}$	ASTM D648
Flammability, UL94	HB @Thickness 1.59 mm	HB @Thickness 0.0625 in	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China