

Techmer ES Plastiblend® ABS 8010

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Extruded

Material Notes:

Availability: North America
Forms: Pellets
Processing Method: Extrusion Blow Molding and Sheet Extrusion
Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Plastiblend-ABS-8010.php

Physical Properties	Metric	English	Comments
Density	1.02 g/cc	0.0368 lb/in ³	ASTM D792
Melt Flow	0.20 g/10 min	0.20 g/10 min	ASTM D1238
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	
	2.3 g/10 min	2.3 g/10 min	ASTM D1238
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	90	90	ASTM D785
Tensile Strength, Yield	31.0 MPa	4500 psi	ASTM D638
Elongation at Break	3.5 %	3.5 %	ASTM D638
Flexural Strength	57.2 MPa	8300 psi	ASTM D790
Flexural Modulus	0.200 GPa	29.0 ksi	ASTM D790
Izod Impact, Notched	1.76 J/cm	3.30 ft-lb/in	ASTM D256
	@Thickness 3.17 mm, Temperature -40.0 °C	@Thickness 0.125 in, Temperature -40.0 °F	
	2.78 J/cm	5.20 ft-lb/in	ASTM D256
	@Thickness 3.17 mm, Temperature 0.000 °C	@Thickness 0.125 in, Temperature 32.0 °F	
	4.22 J/cm	7.90 ft-lb/in	ASTM D256
	@Thickness 3.17 mm, Temperature 22.8 °C	@Thickness 0.125 in, Temperature 73.0 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	93.9 °C	201 °F	Unannealed; ASTM D648

Thermal Properties
(204 psi)

ure at 1.8 MPa

Metric

English

Comments: ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China