

## Techmer ES Plastiblend® ABS CR X

Category : Polymer , Thermoplastic , ABS Polymer

**Material Notes:**

Availability: North America Forms: Pellets Features: Good Chemical Resistance Processing Method: Injection Molding Information provided by TP Composites, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Techmer-ES-Plastiblend-ABS-CR-X.php](http://www.lookpolymers.com/polymer_Techmer-ES-Plastiblend-ABS-CR-X.php)

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage, Flow	0.0050 cm/cm @Thickness 3.17 mm	0.0050 in/in @Thickness 0.125 in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	102	102	ASTM D785
Tensile Strength at Break	33.1 MPa	4800 psi	ASTM D638
Elongation at Break	2.4 %	2.4 %	ASTM D638
Flexural Yield Strength	64.8 MPa	9400 psi	ASTM D790
Flexural Modulus	2.34 GPa	340 ksi	ASTM D790
Izod Impact, Notched	2.40 J/cm @Thickness 3.17 mm	4.50 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 Åµm/m-Å°C	50.0 Åµin/in-Å°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	101 Å°C	214 Å°F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	96.7 Å°C	206 Å°F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China