

Techmer ES Plastiblend® PC/ABS 8001A

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Availability: North America Forms: Pellets Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Plastiblend-PCABS-8001A.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ASTM D792
Water Absorption	0.10 %	0.10 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Melt Flow	8.5 g/10 min	8.5 g/10 min	ASTM D1238
	@Load 3.80 kg, Temperature 230 °C	@Load 8.38 lb, Temperature 446 °F	
	19 g/10 min	19 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 260 °C	@Load 11.0 lb, Temperature 500 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	ASTM D785
Tensile Strength, Yield	56.5 MPa	8200 psi	ASTM D638
Elongation at Break	150 %	150 %	ASTM D638
Flexural Yield Strength	86.2 MPa	12500 psi	ASTM D790
Flexural Modulus	2.34 GPa	340 ksi	ASTM D790
Izod Impact, Notched	6.41 J/cm	12.0 ft-lb/in	ASTM D256
	@Thickness 3.17 mm	@Thickness 0.125 in	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	72.0 µm/m-°C	40.0 µin/in-°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	124 °C	255 °F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China