

Techmer ES Statiblend® HIPS E AS

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Availability: North America Forms: Pellets Additive: Antistatic Features: Antistatic and High Impact Resistance Appearance: Natural Color Information provided by TP Composites, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Techmer-ES-Statiblend-HIPS-E-AS.php

Physical Properties	Metric	English	Comments
Density	1.07 g/cc	0.0387 lb/in ³	ASTM D792
Water Absorption	0.60 % @Time 86400 sec	0.60 % @Time 24.0 hour	ASTM D570
Melt Flow	1.8 g/10 min @Load 5.00 kg, Temperature 200 °C	1.8 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	60	60	ASTM D785
Tensile Strength, Yield	20.0 MPa	2900 psi	ASTM D638
Elongation at Yield	30 %	30 %	ASTM D638
Flexural Yield Strength	28.3 MPa	4100 psi	ASTM D790
Flexural Modulus	1.45 GPa	210 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm @Thickness 3.17 mm	2.00 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	63.0 µm/m-°C	35.0 µin/in-°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	96.1 °C	205 °F	Unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	Unannealed; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments

Volume Resistivity Electrical Properties	1.00e+12 ohm-cm Metric	1.00e+12 ohm-cm English	ASTM D257 Comments
Surface Resistance	1.00e+12 ohm	1.00e+12 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China