

Technetics Group Amicon™ Nylon 6/66 (Unverified Data**)

Category : Polymer , Thermoplastic , Nylon , Nylon 6/66

Material Notes:

Information provided by Technetics Group (formerly Plastomer Technologies)

Order this product through the following link:

http://www.lookpolymers.com/polymer_Technetics-Group-Amicon-Nylon-666-nbspUnverified-Data.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D792
Water Absorption	0.30 %	0.30 %	24 hours; ASTM D570 (2)
Water Absorption at Saturation	7.0 %	7.0 %	ASTM D570 (2)

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	75.8 MPa	11000 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Modulus of Elasticity	2.76 GPa	400 ksi	ASTM D638
Flexural Strength	96.5 MPa	14000 psi	ASTM D790
Flexural Modulus	2.76 GPa	400 ksi	ASTM D790
Compressive Strength	117 MPa	17000 psi	ASTM D695
Izod Impact, Notched	0.320 J/cm	0.600 ft-lb/in	ASTM D256 type "A"
Coefficient of Friction	0.25	0.25	ASTM PTM 55007
K (wear) Factor	145 x 10 ⁻⁸ mm ³ /N-M	72.0 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	QTM 55010
Limiting Pressure Velocity	0.0946 MPa-m/sec	2700 psi-ft/min	4:1 safety factor

Thermal Properties	Metric	English	Comments
CTE, linear	99.0 μm/m-°C	55.0 μin/in-°F	ASTM E-831 (TMA)
	@Temperature 100 °C	@Temperature 212 °F	
Maximum Service Temperature, Air	98.9 °C	210 °F	
Flammability, UL94	HB	HB	ASTM UL-94
	@Thickness 3.17 mm	@Thickness 0.125 in	

Electrical Properties	Metric	English	Comments
Dielectric Constant	4.1	4.1	ASTM D150
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	15.7 kV/mm	400 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China