

## Teknor Apex APEX<sup>®</sup> 1020 Polyvinyl Chloride, Semi-Rigid

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade , PVC, Wire and Cable Grade

### Material Notes:

Notes: 60<sup>°</sup>C General Purpose; RoHS Compliant Uses: Connectors; Grommets; Plugs; Strain Reliefs  
Forms: Pellets Processing Method:

Injection Molding Agency Ratings: UL QMFZ2 .E54709 Wire Types: Molded Components Additional Information: Temperature Rating: 60<sup>°</sup>C

Recognized Component, CSA C22.2 No. 0.6, CSA Flammability Classification: 0.6HB at 0.88mm  
Information Provided by Teknor Apex

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Teknor-Apex-APEX-1020-Polyvinyl-Chloride-Semi-Rigid.php](http://www.lookpolymers.com/polymer_Teknor-Apex-APEX-1020-Polyvinyl-Chloride-Semi-Rigid.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.39 g/cc	1.39 g/cc	ASTM D792
Linear Mold Shrinkage	0.010 - 0.012 cm/cm	0.010 - 0.012 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore C	75	75	10 seconds; ASTM D2240
Tensile Strength at Break	17.2 MPa	2500 psi	ASTM D638
Elongation at Break	160 %	160 %	ASTM D638

Thermal Properties	Metric	English	Comments
Brittleness Temperature	1.00 <sup>°</sup> C	33.8 <sup>°</sup> F	ASTM D746
UL RTI, Electrical	90.0 <sup>°</sup> C	194 <sup>°</sup> F	UL 746
	@Thickness 0.889 mm	@Thickness 0.0350 in	
	90.0 <sup>°</sup> C	194 <sup>°</sup> F	
UL RTI, Mechanical without Impact	90.0 <sup>°</sup> C	194 <sup>°</sup> F	UL 746
	@Thickness 1.20 mm	@Thickness 0.0472 in	
	90.0 <sup>°</sup> C	194 <sup>°</sup> F	
UL RTI, Mechanical without Impact	90.0 <sup>°</sup> C	194 <sup>°</sup> F	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
	90.0 <sup>°</sup> C	194 <sup>°</sup> F	
	HB	HB	

Thermal Properties	Metric	English	Comments
	@Thickness 1.20 mm	@Thickness 0.0472 in	
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	
Oxygen Index	25 %	25 %	ASTM D2863

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	>= 600 V	>= 600 V	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
Hot Wire Ignition, HWI	60 - 120 sec	60 - 120 sec	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	
High Amp Arc Ignition, HAI	60 - 120 arcs	60 - 120 arcs	UL 746
	@Thickness 3.00 mm	@Thickness 0.118 in	

Processing Properties	Metric	English	Comments
Melt Temperature	193 Â°C	380 Â°F	Processing Temperature

Descriptive Properties	Value	Comments
Appearance	Opaque	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China