

Teknor Apex APEX® 6500-70 Polyvinyl Chloride, Flexible

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Flexible Grade , PVC, Wire and Cable Grade

Material Notes:

Notes: 60°C General Purpose; RoHS Compliant Uses: Connectors; Grommets; Plugs; Strain ReliefsForms: Pellets Processing Method: Injection Molding Agency Ratings: UL QMFZ2 .E54709 Wire Types: Molded Components Additional Information: Temperature Rating: 60°CInformation Provided by Teknor Apex

Order this product through the following link:
http://www.lookpolymers.com/polymer_Teknor-Apex-APEX-6500-70-Polyvinyl-Chloride-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Linear Mold Shrinkage	0.015 - 0.018 cm/cm	0.015 - 0.018 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	70	70	15 seconds; ASTM D2240
Tensile Strength at Break	13.1 MPa	1900 psi	ASTM D638
Elongation at Break	450 %	450 %	ASTM D638

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	60.0 °C	140 °F	Continuous Use; ASTM D794
UL RTI, Electrical	50.0 °C @Thickness 1.50 mm	122 °F @Thickness 0.0591 in	UL 746
UL RTI, Mechanical with Impact	50.0 °C @Thickness 1.50 mm	122 °F @Thickness 0.0591 in	UL 746
UL RTI, Mechanical without Impact	50.0 °C @Thickness 1.50 mm	122 °F @Thickness 0.0591 in	UL 746
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Processing Properties	Metric	English	Comments
Melt Temperature	174 °C	345 °F	Processing Temperature

Descriptive Properties	Value	Comments
Appearance	Clear/Transparent	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China