

## Teknor Apex APEX<sup>®</sup> 6500-85 Polyvinyl Chloride, Flexible

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Flexible Grade , PVC, Wire and Cable Grade

### Material Notes:

Notes: 60°C General Purpose; RoHS Compliant Uses: Connectors; Grommets; Plugs; Strain Reliefs  
Forms: Pellets Processing Method: Injection Molding Agency Ratings: UL QMFZ2 .E54709 Wire Types: Molded Components Additional Information: Temperature Rating: 60°C  
Information Provided by Teknor Apex

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Teknor-Apex-APEX-6500-85-Polyvinyl-Chloride-Flexible.php](http://www.lookpolymers.com/polymer_Teknor-Apex-APEX-6500-85-Polyvinyl-Chloride-Flexible.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792
Linear Mold Shrinkage	0.010 - 0.012 cm/cm	0.010 - 0.012 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85	85	15 seconds; ASTM D2240
Tensile Strength at Break	15.0 MPa	2170 psi	ASTM D638
Elongation at Break	250 %	250 %	ASTM D638

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	60.0 °C	140 °F	Continuous Use; ASTM D794
Brittleness Temperature	-20.0 °C	-4.00 °F	ASTM D746
UL RTI, Electrical	50.0 °C @Thickness 1.50 mm	122 °F @Thickness 0.0591 in	UL 746
UL RTI, Mechanical with Impact	50.0 °C @Thickness 1.50 mm	122 °F @Thickness 0.0591 in	UL 746
UL RTI, Mechanical without Impact	50.0 °C @Thickness 1.50 mm	122 °F @Thickness 0.0591 in	UL 746
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	
Oxygen Index	24 %	24 %	ASTM D2863

Processing Properties	Metric	English	Comments
Melt Temperature	191 °C	375 °F	Processing Temperature

Descriptive Properties	Value	Comments
Appearance	Clear/Transparent	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China