

Teknor Apex Flexalloy® 3500-40 Polyvinyl Chloride Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Vinyl (PVC)

Material Notes:

Material Status-Commercial: ActiveAvailability-North AmericaTest Standards Available-ASTM Features: Ultra High MWUses- Tubing, Pump PartsForms-PelletsProcessing- ExtrusionInformation provided by Teknor Apex Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Flexalloy-3500-40-Polyvinyl-Chloride-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.11 g/cc	1.11 g/cc	23°C; ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40	40	15 seconds; ASTM D2240
Tensile Strength, Yield	2.07 MPa	300 psi	100%; ASTM D412
	6.96 MPa	1010 psi	ASTM D412
Elongation at Break	370 %	370 %	ASTM D412
Tear Strength, Total	510.6 N	114.8 lb (f)	Die C; ASTM D1004
Compression Set	12 %	12 %	73°F, 22 hr.; ASTM D395
	57 %	57 %	158°F, 22 hr.; ASTM D395
	70 %	70 %	212°F, 22 hr.; ASTM D395

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-57.0 °C	-70.6 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China