

## Teknor Apex Flexalloy® 3500-65 Polyvinyl Chloride Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Vinyl (PVC)

**Material Notes:**

Material Status-Commercial: ActiveAvailability-North AmericaTest Standards Available-ASTM Features: Ultra High MWUses- Tubing, Pump PartsForms-PelletsProcessing- ExtrusionInformation provided by Teknor Apex Company

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Teknor-Apex-Flexalloy-3500-65-Polyvinyl-Chloride-Elastomer.php](http://www.lookpolymers.com/polymer_Teknor-Apex-Flexalloy-3500-65-Polyvinyl-Chloride-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.17 g/cc	1.17 g/cc	23°C; ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	65	65	15 seconds; ASTM D2240
Tensile Strength, Yield	4.83 MPa	700 psi	100%; ASTM D412
	15.2 MPa	2200 psi	ASTM D412
Elongation at Break	340 %	340 %	ASTM D412
Tear Strength, Total	910.2 N	204.6 lb (f)	Die C; ASTM D1004
Compression Set	16 %	16 %	73°F, 22 hr.; ASTM D395
	55 %	55 %	158°F, 22 hr.; ASTM D395
	60 %	60 %	212°F, 22 hr.; ASTM D395

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-45.0 °C	-49.0 °F	ASTM D746

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China