

## Teknor Apex Flexalloy® 9900-45 Polyvinyl Chloride Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Vinyl (PVC) , PVC, Wire and Cable Grade

**Material Notes:**

Material Status-Commercial: ActiveAvailability-North AmericaTest Standards Available-ASTM Features: Oil Resistant, Ultra High MWUses- Footwear, Tubing, Gaskets, Tools (Power/Others), Hose, Wire and Cable Applications, SealsForms-PelletsProcessing- ExtrusionInformation provided by Teknor Apex Company

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Teknor-Apex-Flexalloy-9900-45-Polyvinyl-Chloride-Elastomer.php](http://www.lookpolymers.com/polymer_Teknor-Apex-Flexalloy-9900-45-Polyvinyl-Chloride-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.11 g/cc	1.11 g/cc	23°C; ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	45	45	15 seconds; ASTM D2240
Tensile Strength, Yield	8.55 MPa	1240 psi	ASTM D412
Elongation at Break	280 %	280 %	ASTM D412
Compression Set	32 %	32 %	158°F, 22 hr.; ASTM D395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	205 °C	401 °F	>60 min.
Brittleness Temperature	-54.0 °C	-65.2 °F	ASTM D746

Descriptive Properties	Value	Comments
Swell	-4%; Oil Immersion, ASTM #3 oil, 125°C, 7 days	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China