

Teknor Apex MF 569 Polyvinyl Chloride, Flexible Film

Category : Polymer , Film , Thermoplastic , Vinyl (PVC) , PVC, Flexible Grade

Material Notes:

Material Status-Commercial: ActiveAvailability-North AmericaTest Standards Available-ASTMUses-Film, Medical Applications Forms-PelletsInformation provided by Teknor Apex Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-MF-569-Polyvinyl-Chloride-Flexible-Film.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.26 g/cc	1.26 g/cc	23°C; ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	78	78	15 seconds; ASTM D2240
Tensile Strength at Break	15.2 MPa	2200 psi	ASTM D412
Tensile Strength, Yield	7.58 MPa	1100 psi	100%; ASTM D412
Elongation at Break	350 %	350 %	ASTM D412

Thermal Properties	Metric	English	Comments
Brittleness Temperature	-33.0 °C	-27.4 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China