

Teknor Apex Monprene® MP-1880 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Uses: Closures; Consumer Applications; Gaskets; Handles; Kitchenware; Medical/Healthcare Applications; Packaging; Safety Equipment; Sporting Goods; Toothbrush Handles; Tubing; Writing Instruments Forms: Pellets Processing Method: Extrusion; Injection Molding

Injection Notes: Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C); Injection Rate:

Fast Extrusion Notes: Screw Speed: 30 to 100 rpm Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Monprene-MP-1880-Thermoplastic-Elastomer.php

| Physical Properties | Metric | English | Comments |
|---------------------|---|---|------------|
| Specific Gravity | 0.870 g/cc | 0.870 g/cc | ASTM D792 |
| Melt Flow | 5.00 g/10 min @Load 2.16 kg, Temperature 125 °C | 5.00 g/10 min @Load 4.76 lb, Temperature 257 °F | ASTM D1238 |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|----------------------------|---------------------------|------------|
| Hardness, Shore A | 2.0 | 2.0 | ASTM D2240 |
| Tensile Strength at Break | 1.24 MPa | 180 psi | ASTM D412 |
| Tensile Stress | 0.241 MPa @Strain 300 % | 35.0 psi @Strain 300 % | ASTM D412 |
| Elongation at Break | 700 % | 700 % | ASTM D412 |

| Processing Properties | Metric | English | Comments |
|---------------------------|--------------|--------------|----------|
| Rear Barrel Temperature | 182 - 232 °C | 360 - 450 °F | |
| Middle Barrel Temperature | 188 - 238 °C | 370 - 460 °F | |
| Front Barrel Temperature | 193 - 243 °C | 380 - 470 °F | |
| Nozzle Temperature | 199 - 249 °C | 390 - 480 °F | |
| Zone 1 | 182 - 232 °C | 360 - 450 °F | |
| Zone 2 | 188 - 238 °C | 370 - 460 °F | |
| Zone 3 | 193 - 243 °C | 380 - 470 °F | |
| Zone 5 | 199 - 249 °C | 390 - 480 °F | |
| Die Temperature | 199 - 249 °C | 390 - 480 °F | |

| Processing Properties | Metric | English | Comments |
|-----------------------|-------------------|-----------------|------------------------|
| Mold Temperature | 35.0 - 48.9 Â°C | 95.0 - 120 Â°F | Processing Temperature |
| Injection Pressure | 1.38 - 5.52 MPa | 200 - 800 psi | |
| Back Pressure | 0.172 - 0.689 MPa | 25.0 - 100 psi | |
| Cushion | 0.381 - 2.54 cm | 0.150 - 1.00 in | |
| Screw Speed | 50 - 100 rpm | 50 - 100 rpm | |

| Descriptive Properties | Value | Comments |
|------------------------|-------------------|----------|
| Appearance | Clear/Transparent | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China