

Teknor Apex Monprene[®] MP-2287M Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Uses: Closures; Consumer Applications; Gaskets; Handles; Kitchenware; Medical/Healthcare Applications; Packaging; Safety Equipment; Sporting Goods; Toothbrush Handles; Tubing; Writing Instruments Forms: Pellets Processing Method: Extrusion; Injection Molding

Injection Notes: Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150[°]F (65[°]C); Injection Rate:

Fast Extrusion Notes: Screw Speed: 30 to 100 rpm Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Monprene-MP-2287M-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.880 g/cc	0.880 g/cc	ASTM D792
Melt Flow	15.0 g/10 min @Load 2.16 kg, Temperature 190 [°] C	15.0 g/10 min @Load 4.76 lb, Temperature 374 [°] F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	19	19	ASTM D2240
Tensile Strength at Break	3.45 MPa	500 psi	ASTM D412
Elongation at Break	650 %	650 %	ASTM D412

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	182 - 232 [°] C	360 - 450 [°] F	
Middle Barrel Temperature	188 - 238 [°] C	370 - 460 [°] F	
Front Barrel Temperature	193 - 243 [°] C	380 - 470 [°] F	
Nozzle Temperature	199 - 249 [°] C	390 - 480 [°] F	
Zone 1	182 - 232 [°] C	360 - 450 [°] F	
Zone 2	188 - 238 [°] C	370 - 460 [°] F	
Zone 3	193 - 243 [°] C	380 - 470 [°] F	
Zone 5	199 - 249 [°] C	390 - 480 [°] F	
Die Temperature	199 - 249 [°] C	390 - 480 [°] F	
Melt Temperature	199 - 249 [°] C	390 - 480 [°] F	Processing Temperature
Mold Temperature	35.0 - 48.9 [°] C	95.0 - 120 [°] F	

Processing Properties	Metric	English	Comments
Injection Pressure	1.38 - 5.52 MPa	200 - 800 psi	
Back Pressure	0.172 - 0.689 MPa	25.0 - 100 psi	
Cushion	0.381 - 2.54 cm	0.150 - 1.00 in	
Screw Speed	50 - 100 rpm	50 - 100 rpm	

Descriptive Properties	Value	Comments
Appearance	Opaque	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China