

## Teknor Apex Monprene® MP-2775 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE

### Material Notes:

Uses: Closures; Consumer Applications; Gaskets; Handles; Kitchenware; Medical/Healthcare Applications; Packaging; Safety Equipment; Sporting Goods; Toothbrush Handles; Tubing; Writing Instruments Forms: Pellets Processing Method: Extrusion; Injection Molding

Injection Notes: Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C); Injection Rate:

Fast Extrusion Notes: Screw Speed: 30 to 100 rpm Information Provided by Teknor Apex

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Teknor-Apex-Monprene-MP-2775-Thermoplastic-Elastomer.php](http://www.lookpolymers.com/polymer_Teknor-Apex-Monprene-MP-2775-Thermoplastic-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.16 g/cc	1.16 g/cc	ASTM D792
Linear Mold Shrinkage	0.0090 cm/cm	0.0090 in/in	ASTM D955
Melt Flow	10.0 g/10 min @Load 2.16 kg, Temperature 230 °C	10.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	ASTM D2240
Tensile Strength at Break	7.58 MPa	1100 psi	ASTM D412
Tensile Stress	3.10 MPa @Strain 300 %	450 psi @Strain 300 %	ASTM D412
Elongation at Break	750 %	750 %	ASTM D412
Compression Set	38 % @Temperature 22.8 °C, Time 79200 sec	38 % @Temperature 73.0 °F, Time 22.0 hour	ASTM D395B

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	182 - 232 °C	360 - 450 °F	
Middle Barrel Temperature	188 - 238 °C	370 - 460 °F	
Front Barrel Temperature	193 - 243 °C	380 - 470 °F	
Nozzle Temperature	199 - 249 °C	390 - 480 °F	
Zone 1	182 - 232 °C	360 - 450 °F	

Zone 2 Processing Properties	188 - 238 Â°C Metric	370 - 460 Â°F English	Comments
Zone 3	193 - 243 Â°C	380 - 470 Â°F	
Zone 5	199 - 249 Â°C	390 - 480 Â°F	
Die Temperature	199 - 249 Â°C	390 - 480 Â°F	
Melt Temperature	199 - 249 Â°C	390 - 480 Â°F	Processing Temperature
Mold Temperature	35.0 - 48.9 Â°C	95.0 - 120 Â°F	
Injection Pressure	1.38 - 5.52 MPa	200 - 800 psi	
Back Pressure	0.172 - 0.689 MPa	25.0 - 100 psi	
Cushion	0.381 - 2.54 cm	0.150 - 1.00 in	
Screw Speed	50 - 100 rpm	50 - 100 rpm	

Descriptive Properties	Value	Comments
Appearance	Opaque	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China