

Teknor Apex Sarlink® 3480 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Olefinic Elastomer (TPO)

Material Notes:

A NSF certified, medium hardness and multi-purpose thermoplastic elastomer (black and natural color) featuring excellent fluid resistance and high temperature performance. It can be processed by injection molding, blow molding or extrusion for applications in contact with potable water, such as pipes, fittings and appurtenances. Processing and Handling (See more in property table) Sarlink® 3480 is a polypropylene based elastomer, which can be processed on conventional thermoplastic equipment for injection molding, extrusion and blow molding. This product has a wide processing window in most applications. Melt temperatures from 360°F to 430°F can be used. Do not exceed 450°F. Drying is recommended for extrusion and blow molding and any time the material is used from an unsealed package. Extrusion screen pack is 20 to 60 mesh. PURGING This product has excellent melt stability. Empty the barrel for idle periods of thirty (30) minutes or longer. Purge thoroughly before and after use of this product with polyethylene or polypropylene. RECYCLING/REGRIND This product can be reprocessed. Physical properties are generally not degraded. Dry regrind prior to reprocessing. COLORING The use of polyolefin based color concentrates is recommended. Apply back pressure in injection molding to disperse color. BONDING/ASSEMBLY STORAGE and HANDLING This product is available in 55 lb. foil lined bags (up to 2,200 lbs. per pallet) or 1,100 lb. polyethylene lined gaylords. It has a storage life at normal temperatures of several years. Please refer to the Material Safety Data Sheet for this grade prior to first time handling. Sarlink® was sold from DSM to Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Sarlink-3480-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Density	0.950 g/cc	0.0343 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	extruded sample; 5 sec. delay; ASTM D2240
	84	84	injection molded sample; 5 sec. delay; ASTM D2240
Tensile Strength at Break	7.10 MPa	1030 psi	Die C; Flow direction; ASTM D412
	9.301 MPa	1349 psi	Die C; Cross direction; ASTM D412
Elongation at Break	430 %	430 %	Die C; Flow direction; ASTM D412
	676 %	676 %	Die C; Cross direction; ASTM D412
100% Modulus	0.00450 GPa	0.653 ksi	Die C; Cross direction; ASTM D412
	0.00510 GPa	0.740 ksi	Die C; Flow direction; ASTM D412
Tear Strength	51.0 kN/m	291 pli	Die C; Cross direction; ASTM D624
Compression Set	32 %	32 %	22h/23°C; ASTM D395B

Mechanical Properties	^{52 %} Metric	^{52 %} English	Comments
	@Temperature 100 °C	@Temperature 212 °F	2200, ASTM D395B

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	182 - 204 °C	360 - 400 °F	Extrusion
	177 - 216 °C	350 - 420 °F	Injection Molding
Middle Barrel Temperature	182 - 204 °C	360 - 400 °F	Extrusion Transition Zone
	177 - 216 °C	350 - 420 °F	Injection Molding
	188 - 210 °C	370 - 410 °F	Extrusion Metering Zone
Front Barrel Temperature	177 - 216 °C	350 - 420 °F	Injection Molding
	188 - 210 °C	370 - 410 °F	Extrusion
Nozzle Temperature	188 - 221 °C	370 - 430 °F	Injection Molding
Die Temperature	193 - 216 °C	380 - 420 °F	Extrusion
Melt Temperature	182 - 221 °C	360 - 430 °F	Injection Molding
	193 - 216 °C	380 - 420 °F	Extrusion
Mold Temperature	10.0 - 65.6 °C	50.0 - 150 °F	Injection Molding
Roll Temperature	21.1 - 48.9 °C	70.0 - 120 °F	Extrusion
Drying Temperature	82.2 °C	180 °F	
Dry Time	3 hour	3 hour	
Injection Pressure	0.0689 - 1.03 MPa	10.0 - 150 psi	Injection Molding Back Pressure
Screw Speed	100 - 200 rpm	100 - 200 rpm	Injection Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China