

## Teknor Apex Sinpolene CPP1030 Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Calcium Carbonate (CaCO3) Filler

**Material Notes:**

Availability: Africa & Middle East; Latin America; Asia Pacific; South America Calcium Carbonate Filler, 30% Filler by Weight Features:

Homopolymer Uses: Appliance Components; Furniture; Housings Forms: Pellets Information Provided by Teknor Apex

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Teknor-Apex-Sinpolene-CPP1030-Polypropylene.php](http://www.lookpolymers.com/polymer_Teknor-Apex-Sinpolene-CPP1030-Polypropylene.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	ASTM D792
Linear Mold Shrinkage	0.0090 cm/cm	0.0090 in/in	ASTM D955
Melt Flow	10.0 g/10 min @Load 2.16 kg, Temperature 230 Â°C	10.0 g/10 min @Load 4.76 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	30.0 MPa	4350 psi	ASTM D638
Flexural Strength	44.0 MPa	6380 psi	ASTM D790
Flexural Modulus	1.92 GPa	278 ksi	ASTM D790
Izod Impact, Notched	0.272 J/cm @Temperature 22.8 Â°C	0.510 ft-lb/in @Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	116 Â°C	241 Â°F	Unannealed; ASTM D648
Vicat Softening Point	148 Â°C	298 Â°F	Loading 1 (10N); ASTM D1525

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China