

Teknor Apex Sinvicomp DBS 8615 Polyvinyl Chloride, Rigid

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Rigid Grade

Material Notes:

Availability: Asia Pacific Features: Good Impact Resistance Uses: Piping Forms: Powder Processing Method: Extrusion Information

Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Sinvicomp-DBS-8615-Polyvinyl-Chloride-Rigid.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.52 g/cc	1.52 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	44.1 MPa	6400 psi	9.8 in/min; ASTM D638
Elongation at Break	120 %	120 %	9.8 in/min; ASTM D638
Izod Impact, Notched	0.390 J/cm	0.730 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	190 °C @Time >=Error in fixSigDigits: @digits must be between 1 a sec	374 °F @Time >=Error in fixSigDigits: @digits must be between 1 a hour	Congo Red; BS 2782
Vicat Softening Point	97.8 °C	208 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China