

Teknor Apex Sinvicomp SIM 6019 Polyvinyl Chloride, Flexible

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Flexible Grade

Material Notes:

Availability: Asia Pacific Features: High Strength Uses: Electrical/Electronic Applications < Forms: Pellets Processing Method: Injection

Molding Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Sinvicomp-SIM-6019-Polyvinyl-Chloride-Flexible.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.31 g/cc	1.31 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	76	76	ASTM D2240
Tensile Strength, Yield	7.4980 MPa	1087.5 psi	Change in tensile strength after 168 hours at 212°F; ASTM D638
	10.0 MPa	1450 psi	9.8 in/min; ASTM D638
Elongation at Break	135 %	135 %	Change after 168 hours at 212°F; ASTM D638
	180 %	180 %	9.8 in/min; ASTM D638

Thermal Properties	Metric	English	Comments
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	BS 2782
	@Temperature 20.0 °C	@Temperature 68.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China