

Teknor Apex **TEKBOND® 6000-35** Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Information provided by Teknor Apex Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-TEKBOND-6000-35-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.980 g/cc	0.980 g/cc	ASTM D792
Linear Mold Shrinkage	0.025 cm/cm	0.025 in/in	
Melt Flow	35 g/10 min @Load 5.00 kg, Temperature 200 °C	35 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	35	35	ASTM D2240
Tensile Strength, Yield	6.21 MPa	900 psi	ASTM D412
Elongation at Break	400 %	400 %	ASTM D412

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China