

Teknor Apex **TEKBOND® MP 1726** Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Information provided by Teknor Apex Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-TEKBOND-MP-1726-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.970 g/cc	0.970 g/cc	ASTM D792
Linear Mold Shrinkage	0.020 cm/cm	0.020 in/in	
Melt Flow	20 g/10 min @Load 5.00 kg, Temperature 200 °C	20 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	50	50	ASTM D2240
Tensile Strength, Yield	7.58 MPa	1100 psi	ASTM D412
Elongation at Break	500 %	500 %	ASTM D412

Thermal Properties	Metric	English	Comments
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China