

Teknor Apex Telcar® TL-2597 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer , TPE

Material Notes:

Uses: Automotive Applications; Automotive Exterior Parts; Automotive Exterior Trim; Automotive Interior Parts; Blow Molding Applications; General Purpose; Grommets; Weatherstripping Forms: Pellets Processing Method: Extrusion; Injection Molding Injection Notes: Injection Rate: Moderate-Fast Extrusion Notes: Screw Speed: 30 to 100 rpm Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Telcar-TL-2597-Thermoplastic-Elastomer.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------|------------|-----------|
| Specific Gravity | 0.930 g/cc | 0.930 g/cc | ASTM D792 |

| Mechanical Properties | Metric | English | Comments |
|---------------------------|---------------|---------------|------------------------|
| Hardness, Shore A | 48 | 48 | 15 seconds; ASTM D2240 |
| | 56 | 56 | ASTM D2240 |
| Tensile Strength at Break | 6.21 MPa | 900 psi | ASTM D412 |
| Tensile Stress | 1.48 MPa | 215 psi | ASTM D412 |
| | @Strain 100 % | @Strain 100 % | |
| Elongation at Break | 700 % | 700 % | ASTM D412 |

| Processing Properties | Metric | English | Comments |
|---------------------------|----------------|---------------|------------------------|
| Rear Barrel Temperature | 171 - 193 °C | 340 - 380 °F | |
| Middle Barrel Temperature | 177 - 199 °C | 350 - 390 °F | |
| Front Barrel Temperature | 182 - 204 °C | 360 - 400 °F | |
| Nozzle Temperature | 188 - 210 °C | 370 - 410 °F | |
| Zone 1 | 166 - 188 °C | 330 - 370 °F | |
| Zone 2 | 171 - 193 °C | 340 - 380 °F | |
| Zone 3 | 177 - 199 °C | 350 - 390 °F | |
| Zone 5 | 182 - 204 °C | 360 - 400 °F | |
| Die Temperature | 190 - 210 °C | 374 - 410 °F | |
| Melt Temperature | 188 - 210 °C | 370 - 410 °F | Processing Temperature |
| Mold Temperature | 25.0 - 65.6 °C | 77.0 - 150 °F | |

| Processing Properties | Metric | English | Comments |
|-----------------------|-------------------|-----------------|----------|
| Injection Pressure | 1.38 - 6.89 MPa | 200 - 1000 psi | |
| Back Pressure | 0.172 - 0.345 MPa | 25.0 - 50.0 psi | |
| Cushion | 0.381 - 2.54 cm | 0.150 - 1.00 in | |
| Screw Speed | 50 - 100 rpm | 50 - 100 rpm | |

| Descriptive Properties | Value | Comments |
|------------------------|--------|----------|
| Appearance | Opaque | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China