

## Teknor Apex Telcar® TL-3954-62 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Vinyl (PVC) , PVC, Wire and Cable Grade

### Material Notes:

Uses: Appliance Wire Insulation; Appliance Wire Jacketing; Cable Jacketing; Connectors; Flexible Cord Jacketing; Industrial Cable Insulation; Terminal Cable Jacketing; Underground Power Cable; Wire and Cable Applications; Wire Jacketing  
 Forms: Pellets Processing  
 Method: Extrusion; Injection Molding  
 Injection Notes: Injection Rate: Moderate-Fast Extrusion Notes: Screw Speed: 30 to 100 rpm  
 Information Provided by Teknor Apex

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Teknor-Apex-Telcar-TL-3954-62-Thermoplastic-Elastomer.php](http://www.lookpolymers.com/polymer_Teknor-Apex-Telcar-TL-3954-62-Thermoplastic-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D792
Melt Flow	1.50 g/10 min @Load 2.16 kg, Temperature 230 °C	1.50 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	62	62	ASTM D2240
Tensile Strength at Break	4.21 MPa	610 psi	ASTM D412
Elongation at Break	720 %	720 %	ASTM D412

Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -60.0 °C	<= -76.0 °F	ASTM D746

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	171 - 193 °C	340 - 380 °F	
Middle Barrel Temperature	177 - 199 °C	350 - 390 °F	
Front Barrel Temperature	182 - 204 °C	360 - 400 °F	
Nozzle Temperature	188 - 210 °C	370 - 410 °F	
Zone 1	166 - 188 °C	330 - 370 °F	
Zone 2	171 - 193 °C	340 - 380 °F	
Zone 3	177 - 199 °C	350 - 390 °F	
Zone 5	182 - 204 °C	360 - 400 °F	

Die Temperature Processing Properties	190 - 210 °C Metric	374 - 410 °F English	Comments
Melt Temperature	188 - 210 °C	370 - 410 °F	Processing Temperature
Mold Temperature	25.0 - 65.6 °C	77.0 - 150 °F	
Injection Pressure	1.38 - 6.89 MPa	200 - 1000 psi	
Back Pressure	0.172 - 0.345 MPa	25.0 - 50.0 psi	
Cushion	0.381 - 2.54 cm	0.150 - 1.00 in	
Screw Speed	50 - 100 rpm	50 - 100 rpm	

Descriptive Properties	Value	Comments
Appearance	Opaque	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China