

Teknor Apex Telcar® TL-8730 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Vinyl (PVC) , PVC, Wire and Cable Grade

Material Notes:

Notes: RoHS Compliant Uses: Appliance Wire Insulation; Appliance Wire Jacketing; Cable Jacketing; Connectors; Flexible Cord Jacketing; Industrial Cable Jacketing; Terminal Cable Jacketing; Underground Power Cable; Wire and Cable Applications; Wire Jacketing Wire Types: SJEOW Agency Ratings: UL 1581; QMTT2.E73402 Forms: Pellets Processing Method: Extrusion; Injection Molding Injection Notes: Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C); Injection Rate: Moderate-Fast Extrusion
Notes: Screw Speed: 30 to 100 rpm Information Provided by Teknor Apex

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-Telcar-TL-8730-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792
Melt Flow	10.0 g/10 min	10.0 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 °C	@Load 11.0 lb, Temperature 392 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	86	86	ASTM D2240
Tensile Strength at Break	10.24 MPa	1485 psi	Change in tensile strength in IRM 902 oil after 168 hours at 140°F; ASTM D471
	11.4 MPa	1650 psi	ASTM D412
	12.51 MPa	1815 psi	Change in tensile strength in air after 168 hours at 277°F; ASTM D573
Elongation at Break	542.8 %	542.8 %	Change in tensile elongation in air after 168 hours at 277°F; ASTM D573
	578.2 %	578.2 %	Change in tensile elongation in IRM 902 oil after 168 hours at 140°F; ASTM D471
	590 %	590 %	ASTM D412

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	105 °C	221 °F	Continuous Use
Brittleness Temperature	-60.0 °C	-76.0 °F	ASTM D746
Oxygen Index	25 %	25 %	ASTM D2863

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	199 - 216 °C	390 - 420 °F	
Middle Barrel Temperature	213 - 221 °C	415 - 430 °F	
Front Barrel Temperature	221 - 227 °C	430 - 440 °F	
Nozzle Temperature	221 - 229 °C	430 - 445 °F	
Zone 1	193 - 210 °C	380 - 410 °F	
Zone 2	199 - 216 °C	390 - 420 °F	
Zone 3	213 - 221 °C	415 - 430 °F	
Zone 5	221 - 227 °C	430 - 440 °F	
Die Temperature	221 - 229 °C	430 - 445 °F	
Melt Temperature	221 - 229 °C	430 - 445 °F	Processing Temperature
Mold Temperature	25.0 - 65.6 °C	77.0 - 150 °F	
Injection Pressure	1.38 - 6.89 MPa	200 - 1000 psi	
Back Pressure	0.172 - 0.345 MPa	25.0 - 50.0 psi	
Cushion	0.381 - 2.54 cm	0.150 - 1.00 in	
Screw Speed	50 - 100 rpm	50 - 100 rpm	

Descriptive Properties	Value	Comments
Appearance	Opaque	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China