

## Teknor Apex Telcar® TL-8732R Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer , TPE

### Material Notes:

Notes: RoHS Compliant Uses: Automotive Applications; Automotive Exterior Parts; Automotive Exterior Trim; Automotive Interior Parts; Blow Molding Applications; General Purpose; Grommets; Weatherstripping Agency Ratings: UL 1581 Forms: Pellets Processing Method: Extrusion; Injection Molding Injection Notes: Injection Rate: Moderate-Fast Extrusion Notes: Screw Speed: 30 to 100 rpm Information Provided by Teknor Apex

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Teknor-Apex-Telcar-TL-8732R-Thermoplastic-Elastomer.php](http://www.lookpolymers.com/polymer_Teknor-Apex-Telcar-TL-8732R-Thermoplastic-Elastomer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.17 g/cc	1.17 g/cc	ASTM D792
Melt Flow	14.0 g/10 min @Load 5.00 kg, Temperature 200 °C	14.0 g/10 min @Load 11.0 lb, Temperature 392 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	ASTM D2240
Tensile Strength at Break	11.7 MPa	1700 psi	ASTM D412
Elongation at Break	600 %	600 %	ASTM D412

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	105 °C	221 °F	Continuous Use
Brittleness Temperature	<= -60.0 °C	<= -76.0 °F	ASTM D746
Flammability, UL94	V-2	V-2	QMTT2.E73409
Oxygen Index	23 %	23 %	ASTM D2863

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.3 @Frequency 1000 Hz	2.3 @Frequency 1000 Hz	ASTM D150

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	171 - 193 °C	340 - 380 °F	
Middle Barrel Temperature	177 - 199 °C	350 - 390 °F	

Front Barrel Temperature Processing Properties	182 - 204 °C Metric	360 - 400 °F English	Comments
Nozzle Temperature	188 - 210 °C	370 - 410 °F	
Zone 1	166 - 188 °C	330 - 370 °F	
Zone 2	171 - 193 °C	340 - 380 °F	
Zone 3	177 - 199 °C	350 - 390 °F	
Zone 5	182 - 204 °C	360 - 400 °F	
Die Temperature	190 - 210 °C	374 - 410 °F	
Melt Temperature	188 - 210 °C	370 - 410 °F	Processing Temperature
Mold Temperature	25.0 - 65.6 °C	77.0 - 150 °F	
Injection Pressure	1.38 - 6.89 MPa	200 - 1000 psi	
Back Pressure	0.172 - 0.345 MPa	25.0 - 50.0 psi	
Cushion	0.381 - 2.54 cm	0.150 - 1.00 in	
Screw Speed	50 - 100 rpm	50 - 100 rpm	

Descriptive Properties	Value	Comments
Appearance	Opaque	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China