

## Teknor Apex TruVis Esters™ DIOA Di-IsoOctyl Adipate

Category : Polymer

Material Notes:

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Teknor-Apex-TruVis-Esters-DIOA-Di-IsoOctyl-Adipate.php](http://www.lookpolymers.com/polymer_Teknor-Apex-TruVis-Esters-DIOA-Di-IsoOctyl-Adipate.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.929 g/cc	0.929 g/cc	
Viscosity	2.7 cP	2.7 cP	
	@Temperature 100 °C	@Temperature 212 °F	
Viscosity	9.1 cP	9.1 cP	
	@Temperature 40.0 °C	@Temperature 104 °F	
Viscosity Measurement	144	144	Viscosity Index

Thermal Properties	Metric	English	Comments
Pour Point	-67.0 °C	-88.6 °F	
Flash Point	191 °C	376 °F	

Chemical Properties	Metric	English	Comments
Acid Value	<= 0.050	<= 0.050	mg KOH/g

Descriptive Properties	Value	Comments
Appearance	Clear	
Color	50	Pt/Co Scale
Ester Content (%), min	99	
Moisture (ppm), max	500	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

