

Teknor Apex TruVis Esters™ DTDA Di-Tridecyl Adipate

Category : Polymer

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-TruVis-Esters-DTDA-Di-Tridecyl-Adipate.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.915 g/cc	0.915 g/cc	
Viscosity	5.3 cP	5.3 cP	
	@Temperature 100 °C	@Temperature 212 °F	
Viscosity	25 cP	25 cP	
	@Temperature 40.0 °C	@Temperature 104 °F	
Viscosity Measurement	153	153	Viscosity Index

Thermal Properties	Metric	English	Comments
Pour Point	-55.0 °C	-67.0 °F	
Flash Point	260 °C	500 °F	

Chemical Properties	Metric	English	Comments
Acid Value	<= 0.050	<= 0.050	mg KOH/g

Descriptive Properties	Value	Comments
Appearance	Clear	
Color	100	Pt/Co Scale
Ester Content (%), min	99	
Moisture (ppm), max	500	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China

