

Teknor Apex UNIPRENE® 7010-55 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Information provided by Teknor Apex Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-UNIPRENE-7010-55-Thermoplastic-Elastomer.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------|------------|-----------|
| Specific Gravity | 0.960 g/cc | 0.960 g/cc | ASTM D792 |

| Mechanical Properties | Metric | English | Comments |
|-------------------------|-------------|-----------|------------------------------------|
| Hardness, Shore A | 55 | 55 | 5 seconds; ASTM D2240 |
| Tensile Strength, Yield | 3.72 MPa | 540 psi | ASTM D412 |
| Elongation at Break | 300 % | 300 % | ASTM D412 |
| 100% Modulus | 0.00207 GPa | 0.300 ksi | ASTM D412 |
| Tear Strength | 19.3 kN/m | 110 pli | ASTM D624 |
| Compression Set | 22 % | 22 % | 23°C, 22 hr.; ASTM D395, Method B |
| | 42 % | 42 % | 100°C, 22 hr.; ASTM D395, Method B |

| Thermal Properties | Metric | English | Comments |
|-------------------------|-------------|-------------|-----------|
| Brittleness Temperature | <= -60.0 °C | <= -76.0 °F | ASTM D746 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China