

Teknor Apex UNIPRENE® 7010-73 Thermoplastic Elastomer

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

Information provided by Teknor Apex Company

Order this product through the following link:

http://www.lookpolymers.com/polymer_Teknor-Apex-UNIPRENE-7010-73-Thermoplastic-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.960 g/cc	0.960 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	73	73	5 seconds; ASTM D2240
Tensile Strength, Yield	6.55 MPa	950 psi	ASTM D412
Elongation at Break	380 %	380 %	ASTM D412
100% Modulus	0.00359 GPa	0.520 ksi	ASTM D412
Tear Strength	33.3 kN/m	190 pli	ASTM D624
Compression Set	28 %	28 %	23°C, 22 hr.; ASTM D395, Method B
	52 %	52 %	100°C, 22 hr.; ASTM D395, Method B

Thermal Properties	Metric	English	Comments
Brittleness Temperature	<= -60.0 °C	<= -76.0 °F	ASTM D746

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China