

Thermoseal KLINGERSIL® C-4408 Metal Reinforced Gasketing

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Synthetic Fiber Nitrile Binder High Temperature & Stress Fluctuating Temperatures & Pressures Vibration Low Carbon Steel Woven Mesh
Insert Information provided by Thermoseal Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Thermoseal-KLINGERSIL-C-4408-Metal-Reinforced-Gasketing.php

Physical Properties	Metric	English	Comments
Density	1.90 g/cc	0.0686 lb/in ³	ASTM F1315
Thickness	1588 microns	62.52 mil	Thickness tested

Descriptive Properties	Value	Comments
Color	Black	(Top/Bottom)
Compressibility	8 percent	ASTM F36J
Creep Relaxation	20 percent	1/32", ASTM F38B
Klinger Hot Compression Test	10 percent	Initial, Thickness Decrease 73°F (23°C)
	22 percent	Additional, Thickness Decrease 572°F (300°C)
Recovery	>50 percent	ASTM F36J
Thickness Increase	0-5%	ASTM F146 after immersion in ASTM Oil 1, 5h/300°F (149°C)
	0-5%	ASTM Oil IRM903, 5h/300°F (149°C)
	0-5%	ASTM Fuel A, 5h/73°F (23°C)
	0-5%	ASTM Fuel B, 5h/73°F (23°C)
Weight Increase	<10%	ASTM F146 after immersion in Fuel B 5h/73°F (23°C)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China