

Thermoseal KLINGERSIL® C-4433 Compressed Inorganic Fiber Sheet

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Fiberglass, Aramid & Inorganic Fibers
Nitrile Binder
Ultimate Steam Sheet
Outstanding Load Bearing
Excellent Creep Relaxation
Best General Purpose Sheet
Information provided by Thermoseal Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Thermoseal-KLINGERSIL-C-4433-Compressed-Inorganic-Fiber-Sheet.php

Physical Properties	Metric	English	Comments
Density	1.80 g/cc	0.0650 lb/in ³	ASTM F1315
Thickness	1588 microns	62.52 mil	Thickness tested

Electrical Properties	Metric	English	Comments
Dielectric Strength	21.0 kV/mm	533 kV/in	ASTM D149-95a

Descriptive Properties	Value	Comments
Color	Red	(Top/Bottom)
Compressibility	7 percent	ASTM F36J
Creep Relaxation	20 percent	1/32", ASTM F38B
Gas Permeability	<0.2 ml/min	DIN 3535/6
Klinger Hot Compression Test	7 percent	Initial, Thickness Decrease 73°F (23°C)
	8 percent	Additional, Thickness Decrease 572°F (300°C)
Leachable Chloride Content	150 ppm	FSA Method (Typical)
Recovery	>60 percent	ASTM F36J
Sealability	<0.5 ml/hr	1/32", ASTM F37A
Thickness Increase	0-4%	ASTM Oil IRM903, 5h/300°F (149°C)
	0-5%	ASTM F146 after immersion in ASTM Oil 1, 5h/300°F (149°C)
	0-5%	ASTM Fuel A, 5h/73°F (23°C)
	0-7%	ASTM Fuel B, 5h/73°F (23°C)
Weight Increase	<10%	ASTM F146 after immersion in Fuel B 5h/73°F (23°C)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China