

Thermoseal KLINGERSIL® C-4509 Metal Reinforced Gasketing

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Carbon FiberNitrile BinderGood in High Load ApplicationsVibrationGalvanized Low Carbon Steel InsertInformation provided by Thermoseal Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Thermoseal-KLINGERSIL-C-4509-Metal-Reinforced-Gasketing.php

Physical Properties	Metric	English	Comments
Density	2.00 g/cc	0.0723 lb/in ³	ASTM F1315
Thickness	1588 microns	62.52 mil	Thickness tested

Descriptive Properties	Value	Comments
Color	Black	(Top/Bottom)
Compressibility	12 percent	ASTM F36J
Creep Relaxation	20 percent	1/32", ASTM F38B
Klinger Hot Compression Test	7 percent	Additional, Thickness Decrease 572°F (300°C)
	9 percent	Initial, Thickness Decrease 73°F (23°C)
Recovery	>70 percent	ASTM F36J
Thickness Increase	0-3%	ASTM Oil IRM903, 5h/300°F (149°C)
	0-5%	ASTM F146 after immersion in ASTM Oil 1, 5h/300°F (149°C)
	0-5%	ASTM Fuel A, 5h/73°F (23°C)
	0-5%	ASTM Fuel B, 5h/73°F (23°C)
Weight Increase	<9%	ASTM F146 after immersion in Fuel B 5h/73°F (23°C)

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China