

## ThyssenKrupp XABO® 460 T Structural Steel

Category : Metal , Ferrous Metal , Carbon Steel , Low Carbon Steel

### Material Notes:

This Material Specification applies to thermo mechanically rolled flat products in thicknesses up to 60 mm. The criteria to distinguish the steel grades is the lowest test temperature for the notch-bar impact test. Application: These steels are applied in welded constructions such as supporting structures, vessels etc., where a secured prevention against cold cracking in the welded joints is required. Due to the low carbon equivalent, these steels are highly resistant against cold cracking. Information Provided by Thyssen Krupp

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ThyssenKrupp-XABO-460-T-Structural-Steel.php](http://www.lookpolymers.com/polymer_ThyssenKrupp-XABO-460-T-Structural-Steel.php)

Physical Properties	Metric	English	Comments
Density	7.85 g/cc	0.284 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	530 - 720 MPa	76900 - 104000 psi	
Tensile Strength, Yield	>= 420 MPa	>= 60900 psi	50<x=60mm
	>= 440 MPa	>= 63800 psi	35<x=50mm
	>= 460 MPa	>= 66700 psi	
	@Thickness 35.0 mm	@Thickness 1.38 in	
Elongation at Break	>= 17 %	>= 17 %	
Modulus of Elasticity	213 GPa	30900 ksi	
Charpy Impact	16.0 J	11.8 ft-lb	Transverse
	@Temperature -50.0 °C	@Temperature -58.0 °F	
	25.0 J	18.4 ft-lb	Transverse
	@Temperature -40.0 °C	@Temperature -40.0 °F	
	27.0 J	19.9 ft-lb	Longitudinal
	@Temperature -50.0 °C	@Temperature -58.0 °F	
	35.0 J	25.8 ft-lb	Transverse
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	40.0 J	29.5 ft-lb	Longitudinal
	@Temperature -40.0 °C	@Temperature -40.0 °F	
	45.0 J	33.2 ft-lb	Transverse

Mechanical Properties	@Temperature -20.0 °C Metric	@Temperature -4.00 °F English	Comments
	50.0 J	36.9 ft-lb	Longitudinal
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	65.0 J	47.9 ft-lb	Longitudinal
	@Temperature -20.0 °C	@Temperature -4.00 °F	

Thermal Properties	Metric	English	Comments
Specific Heat Capacity	0.450 J/g-°C	0.108 BTU/lb-°F	
Thermal Conductivity	45.0 W/m-K	312 BTU-in/hr-ft <sup>2</sup> -°F	

Component Elements Properties	Metric	English	Comments
Carbon, C	<= 0.14 %	<= 0.14 %	
Copper, Cu	<= 0.30 %	<= 0.30 %	
Manganese, Mn	<= 1.7 %	<= 1.7 %	
Nickel, Ni	<= 0.40 %	<= 0.40 %	
Niobium, Nb (Columbium, Cb)	<= 0.050 %	<= 0.050 %	
Other	<= 0.45 %	<= 0.45 %	Carbon Equivalent
Phosphorous, P	<= 0.025 %	<= 0.025 %	
Silicon, Si	<= 0.50 %	<= 0.50 %	
Sulfur, S	<= 0.010 %	<= 0.010 %	

Electrical Properties	Metric	English	Comments
Volume Resistivity	0.000030 ohm-cm	0.000030 ohm-cm	

Descriptive Properties	Value	Comments
Magnetic Properties	magnetizable	
Thermal diffusivity (cm <sup>2</sup> /s)	0.13	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China